



## **Technical Data Sheet**



**Grade: RAVLEK 100 CPE**

### **Chlorinated Polyethylene (CPE) Impact Modifier**

#### **Application**

Window profiles, door frames, sidings/cladding, pipes and sheet.

#### **Features**

CPE Impact Modifiers show excellent impact properties with flame retardancy.

<b>Basic Properties</b>	
Chlorine content (%)	35±2
Volatiles (%)	0.4
Residue on sieve, 0.9mm sieve (%)	2.0
Shore hardness (A)	70
Apparent density (g/ml)	0.48 – 0.52
Tensile strength (Mpa)	8.0
Remaining Crystallinity	5%

#### **Packaging**

We offer 25kg bags and bulk bags

*The above results are typical values and do not constitute a specification.*

Please call for further information on any of our products

**Telephone: +44 20 88 16 81 25**