



Technical Data Sheet



Grade: RAVLEK 146 CPE

Chlorinated Polyethylene (CPE) Impact Modifier

Application

Window profiles, door frames, sidings/cladding, pipes and sheet.

Features

CPE Impact Modifiers show excellent impact properties with flame retardancy.

Basic Properties	
Chlorine content (%)	35
Volatiles (%)	<0.5
Residue on sieve, 0.9mm sieve (%)	<2.0
Shore hardness (A)	<65
Apparent density (g/ml)	>0.50
Tensile strength (Mpa)	>8
Remaining Crystallinity	<2

Packaging

We offer 25kg bags and bulk bags

The above results are typical values and do not constitute a specification.

Please call for further information on any of our products

Telephone: +44 20 88 16 81 25