



**ALPHA**  
PLASTIC CHEMICALS

**TECHNICAL DATA SHEET**



**MANLON C30**

**Application**

Sheet, film etc.

**Feature**

Transparent impact modifiers improve impact strength of transparent PVC product. APC has several grades with different combination of impact strength and transparency.

**Properties**

Properties	Condition	Unit	Value
<b>Bulk Density</b>	23±2°C	g/cc	>0.32
<b>Volatiles</b>	110±2°C	Wt%	< 1
<b>IZOD Impact strength</b>	23°C	Kg·cm/cm	>75
	-10°C	Kg·cm/cm	>75

The above results are typical values and do not constitute a specification.